

TECHNICAL DATA SHEET

AL 90 Stipple Finish

|--|

AL90 Stipple Finish is a specially developed, flexible 100% acrylic resin emulsion roll-on texture coating. Formulated using high-durability acrylic resins blended with highest quality calcium carbonates and high purity quartz sands.

AL90 Stipple Finish provides a soft matt finish, with an even stippled texture appearance for ceilings and concrete soffits.

Features & Performance Qualities

- > Excellent adhesion properties.
- Flexible, impact resistant, highly water-resistant roll-on finish.
- Mould Resist
- Uniform, matt texture finish.
- > Moisture vapour permeable
- Ready to use.

Uses

- > AL90 Stipple Finish is designed for application over suitably prepared Concrete ceilings and soffits.
- > Suitable for use both internally and externally.

Typical product data

(@ 25°C and 50% Relative Humidity)

Coverage: 30 - 40m² / 15Lt. per coat

Drying/Curing: 6-8 Hours

Over-coating: Can be over-coated after min. 4 hours curing.

Touch Dry: approx. 1 Hour

Dry Film Thickness:

Colour: Available in White Base only (Tint using universal tinters for water-based products.)

Packaging: 15Lt Bucket.

Clean-up: Clean with water.

SUPA COAT AUSTRALIA PTY. LTD. ABN: 87 054 216 232 Cnr Fritz Rd. & Bruce Hwy Gympie Qld 4570 www.supacoat.com.au info@supacoat.com.au Ph: +61 7 5482 8263



TECHNICAL DATA SHEET

AL 90 Stipple Finish

At 70 slipple i ii iisi
Application
AL90 Stipple Finish is designed for application with long Nap and/or Texture roller sleeves.
• Ensure substrate is of sound nature, free from dust, dirt, loose particles and/or any other contaminants which may affect adhesion of subsequent coatings.
Stir prior to application.
Apply product with a chosen paint roller. Ensure to keep a wet-edge during application process.
 Apply a minimum of 2 coats to achieve optimum coverage and texture uniformity. (Observe recommended drying times between coats.)
Precautions and Limitations.
AL 90 Stipple Finish should not be applied in temperatures below 5°C or above 35°C. Avoid application in extremely windy conditions.
Protect from rain for up to 24hrs after application. (Depending on Climatic conditions.)
AL 90 Stipple Finish should not be applied over hot substrates, as workability and quality of finish may be affected
AL 90 Stipple Finish is not suitable for application to areas of sustained damp, or areas submerged in water.
Transport, Storage & Handling
Store containers in a cool place, out of direct sunlight.
Protect product form freezing and extreme heat. Keep stored between 5°C - 35°C.
Do not stack over 3 drums high.
Disclaimer
Any advice, recommendations, information, assistance, or service provided by SUPA COAT AUSTRALIA PTY. LTD. Its

Any advice, recommendations, information, assistance, or service provided by SUPA COAT AUSTRALIA PTY. LTD. Its staff or consultants in relation to products, their use and application is given in good faith and is believed by SUPA COAT AUSTRALIA PTY. LTD. to be appropriate and accurate. SUPA COAT AUSTRALIA PTY. LTD. will not accept responsibility for any misuse product/s or if not applied by suitably qualified, skilled and experienced persons and not in accordance with technical specifications. SUPA COAT technical information is correct at time of publication, however due to continuing product improvement, SUPA COAT AUSTRALIA PTY. LTD. reserves its right to change technical information without notice. It remains the sole responsibility of user to ensure information is current prior to use.